





## WOODACOUSTICS

Strip Type  
2 / 14 / V4




Sound Absorber Coefficient	Frequency (Hz)				NRC
	125	250	500	1K	
— Type A	0.13	0.13	0.09	0.06	0.10
— Type B	0.29	0.71	0.97	0.67	0.66
— Type C	0.44	0.90	0.91	0.57	0.71
— Type D	0.57	0.95	0.73	0.63	0.72
— Type E	0.32	0.81	0.93	0.78	0.71




## WOODACOUSTICS


Strip Type  
3/5/1/4



Absorption Coefficients Curve





Sound Absorber Coefficient	1/3 Center Frequency Analysis (Hz)					
	125	250	500	1K	2K	4K
— Type A	0.12	0.41	0.83	1.12	0.70	0.62
— Type B	0.73	0.62	0.69	0.72	0.72	0.73




# WOODACOUSTICS

Strip Type  
3 / 13 / V4




Sound Absorber Coefficient	1/3 Center Frequency Analysis (Hz)					
	125	250	500	1K	2K	4K
Type A	0.12	0.41	0.81	1.16	0.89	0.66
Type B	0.69	0.72	0.83	0.74	0.83	0.76




# WOODACOUSTICS


Strip Type  
3 / 30 / V4



Absorption Coefficients Curve





Sound Absorber Coefficient	Frequency (Hz)				NRC
	125	250	500	1K	
— Type A	0.15	0.11	0.09	0.09	0.11
— Type B	0.30	0.83	0.85	0.66	0.66
— Type C	0.58	0.94	0.75	0.57	0.71
— Type D	0.64	0.86	0.64	0.47	0.65
— Type E	0.30	0.75	0.90	0.78	0.68



## WOODACOUSTICS

Diffusion Type  
95 / 190 / 100



Sound Absorber Coefficient	1/3 Center Frequency Analysis (Hz)					
	125	250	500	1K	2K	4K
— A型	0.33	0.58	0.70	0.35	0.26	0.25